

Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 1 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

以下測試樣品係由申請廠商所提供及確認 (The following sample(s) was/were submitted and identified by the applicant as):

樣品名稱(Sample Name) : COPPER LEAD FRAME (銅合金導線架)

樣品型號(Style/Item No.) : C7025

收件日(Sample Receiving Date)

: 23-Sep-2022

測試期間(Testing Period)

23-Sep-2022 to 03-Oct-2022

測試需求(Test Requested) :

(1) 依據客戶指定、參考RoHS 2011/65/EU Annex II及其修訂指令(EU) 2015/863測試 鎘、鉛、汞、六價鉻、多溴聯苯、多溴聯苯醚, DBP, BBP, DEHP, DIBP。 (As specified by client, with reference to RoHS 2011/65/EU Annex II and amending Directive (EU) 2015/863 to determine Cadmium, Lead, Mercury, Cr(VI), PBBs, PBDEs, DBP, BBP, DEHP, DIBP contents in the submitted sample(s).)

(2) 其他測試項目請見下一頁。 (Please refer to next pages for the other item(s).)

測試結果(Test Results) 結 論(Conclusion) 請參閱下一頁 (Please refer to following pages.)

(1) 根據客戶所提供的樣品·其鎘、鉛、汞、六價鉻、多溴聯苯、多溴聯苯醚, DBP, BBP, DEHP, DIBP的測試結果符合RoHS 2011/65/EU Annex II暨其修訂指令(EU) 2015/863之限值要求。 (Based on the performed tests on submitted sample(s), the test results of Cadmium, Lead, Mercury, Cr(VI), PBBs, PBDEs, DBP, BBP, DEHP, DIBP comply with the limits as set by RoHS Directive (EU) 2015/863 amending Annex II to Directive 2011/65/EU.)

Troy Chang / Department Malager
Signed for and on behalf of Alwahi
SGS TAIWAN LTD.
Chemical Laboratory - Taipei



PIN CODE: E01C4C09



Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 2 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

測試部位敘述 (Test Part Description)

No.1 : 銅色金屬底材 (C7025) (BASE MATERIAL OF COPPER COLORED METAL (C7025))

測試結果 (Test Results)

測試項目	測試方法	單位	MDL	結果	限值
(Test Items)	(Method)	(Unit)		(Result)	(Limit)
				No.1	
鎘 (Cd) (Cadmium (Cd)) (CAS No.: 7440-	參考IEC 62321-5: 2013,以感應耦合電漿	mg/kg	2	n.d.	100
43-9)	發射光譜儀分析。(With reference to IEC				
	62321-5: 2013, analysis was performed				
	by ICP-OES.)				
鉛 (Pb) (Lead (Pb)) (CAS No.: 7439-92-1)	參考IEC 62321-5: 2013 · 以感應耦合電漿	mg/kg	2	43.5	1000
	發射光譜儀分析。(With reference to IEC				
	62321-5: 2013, analysis was performed				
	by ICP-OES.)				
汞 (Hg) (Mercury (Hg)) (CAS No.: 7439-	參考IEC 62321-4: 2013+ AMD1: 2017 ·	mg/kg	2	n.d.	1000
97-6)	以感應耦合電漿發射光譜儀分析。(With				
	reference to IEC 62321-4: 2013+ AMD1:				
	2017, analysis was performed by ICP-				
	OES.)				
六價鉻 (Hexavalent Chromium) Cr(VI)	參考IEC 62321-7-1: 2015,以紫外光-可見	μg/cm²	0.1	n.d.	-
(CAS No.: 18540-29-9) (#2)	光分光光度計分析。(With reference to				
	IEC 62321-7-1: 2015, analysis was				
	performed by UV-VIS.)				
六價鉻 Cr(VI) (Hexavalent Chromium	參考IEC 62321-7-2: 2017,以紫外光-可見	mg/kg	8	n.d.	-
Cr(VI)) (CAS No.: 18540-29-9)	光分光光度計分析。(With reference to				
	IEC 62321-7-2: 2017, analysis was				
	performed by UV-VIS.)				



Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 3 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

(Method)	(Unit)			
	(Unit)		(Result)	(Limit)
			No.1	
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
參考IEC 62321-6: 2015,以氣相層析儀/質	mg/kg	5	n.d.	-
譜儀分析。(With reference to IEC 62321-	mg/kg	ı	n.d.	1000
6: 2015, analysis was performed by	mg/kg	5	n.d.	-
GC/MS.)	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	5	n.d.	-
	mg/kg	ı	n.d.	1000
參考IEC 62321: 2008‧以氣相層析儀/質譜儀分析。(With reference to IEC 62321: 2008, analysis was performed by GC/MS.)	mg/kg	5	n.d.	-
	譜儀分析。(With reference to IEC 62321-6: 2015, analysis was performed by GC/MS.) 参考IEC 62321: 2008·以氣相層析儀/質譜儀分析。(With reference to IEC 62321: 2008, analysis was performed by	mg/kg	Mg/kg 5 mg	Mg/kg 5 n.d. m



Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 4 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

測試項目	測試方法	單位	MDL	結果	限值
(Test Items)	(Method)	(Unit)		(Result)	(Limit)
				No.1	
氟 (F) (Fluorine (F)) (CAS No.: 14762-94-		mg/kg	50	n.d.	-
8)					
氯 (Cl) (Chlorine (Cl)) (CAS No.: 22537-	參考BS EN 14582: 2016,以離子層析儀分	mg/kg	50	n.d.	-
15-1)	析。(With reference to BS EN 14582:				
溴 (Br) (Bromine (Br)) (CAS No.: 10097-	2016, analysis was performed by IC.)	mg/kg	50	n.d.	-
32-2)					
碘 (I) (Iodine (I)) (CAS No.: 14362-44-8)		mg/kg	50	n.d.	-
全氟辛烷磺酸及其鹽類 (PFOS and its	參考CEN/TS 15968: 2010 · 以液相層析串	mg/kg	0.01	n.d.	-
salts) (CAS No.: 1763-23-1 and its salts)	聯質譜儀分析。(With reference to				
	CEN/TS 15968: 2010, analysis was				
	performed by LC/MS/MS.)				
全氟辛酸及其鹽類 (PFOA and its salts)	参考CEN/TS 15968: 2010,以液相層析串	mg/kg	0.01	n.d.	-
(CAS No.: 335-67-1 and its salts)	聯質譜儀分析。(With reference to				
	CEN/TS 15968: 2010, analysis was				
	performed by LC/MS/MS.)				
多氯聯苯 (PCBs) (Polychlorinated	参考US EPA 3550C: 2007,以氣相層析儀/	mg/kg	0.5	n.d.	-
biphenyls (PCBs))	質譜儀分析。(With reference to US EPA				
	3550C: 2007, analysis was performed by				
	GC/MS.)				
多氯奈 (PCNs) (Polychlorinated	參考US EPA 3550C: 2007 · 以氣相層析儀/	mg/kg	5	n.d.	-
naphthalene (PCNs))	質譜儀分析。(With reference to US EPA				
	3550C: 2007, analysis was performed by				
	GC/MS.)				
多氯三聯苯 (PCTs) (Polychlorinated	參考US EPA 3550C: 2007,以氣相層析儀/	mg/kg	0.5	n.d.	-
terphenyls (PCTs))	質譜儀分析。(With reference to US EPA				
	3550C: 2007, analysis was performed by				
与	GC/MS.)				
短鏈氯化石蠟(C10-C13) (SCCP) (Short	參考ISO 18219: 2015 · 以氣相層析儀/質	mg/kg	50	n.d.	-
Chain Chlorinated Paraffins(C10-C13)	譜儀分析。(With reference to ISO 18219:				
(SCCP)) (CAS No.: 85535-84-8)	2015, analysis was performed by				
	GC/MS.)				



Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 5 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

測試項目	測試方法	單位	MDL	結果	限值
(Test Items)	(Method)	(Unit)		(Result)	(Limit)
				No.1	
三丁基錫 (TBT) (Tributyl tin (TBT))	參考ISO 17353: 2004 · 以氣相層析儀/火	mg/kg	0.03	n.d.	-
	焰光度偵測器分析。(With reference to				
	ISO 17353: 2004, analysis was				
	performed by GC/FPD.)				
氧化雙三丁基錫 (TBTO) (Bis(tributyltin)	由三丁基錫測試結果計算得之。	mg/kg	0.03 ▲	n.d.	-
oxide (TBTO)) (CAS No.: 56-35-9)	(Calculated from the result of Tributyl				
	Tin (TBT).)				
三苯基錫 (TPT) (Triphenyl tin (TPT))	參考ISO 17353: 2004,以氣相層析儀/火	mg/kg	0.03	n.d.	-
	焰光度偵測器分析。(With reference to				
	ISO 17353: 2004, analysis was				
	performed by GC/FPD.)				
二丁基錫 (DBT) (Dibutyl tin (DBT))	參考ISO 17353: 2004,以氣相層析儀/火	mg/kg	0.03	n.d.	-
	焰光度偵測器分析。(With reference to				
	ISO 17353: 2004, analysis was				
	performed by GC/FPD.)				
二辛基錫 (DOT) (Dioctyl tin (DOT))	參考ISO 17353: 2004 · 以氣相層析儀/火	mg/kg	0.03	n.d.	-
	焰光度偵測器分析。(With reference to				
	ISO 17353: 2004, analysis was				
	performed by GC/FPD.)				
銻 (Sb) (Antimony (Sb)) (CAS No.: 7440-	参考US EPA 3050B: 1996,以感應耦合電	mg/kg	2	n.d.	-
36-0)	漿發射光譜儀分析。(With reference to				
	US EPA 3050B: 1996, analysis was				
	performed by ICP-OES.)				
三氧化二銻 (Sb ₂ O ₃) (Antimony trioxide	由銻結果計算得之。(Calculated from the	mg/kg	2▲	n.d.	-
(Sb ₂ O ₃)) (CAS No.: 1309-64-4)	result of Antimony.)				
鈹 (Be) (Beryllium (Be)) (CAS No.: 7440-	参考US EPA 3050B: 1996,以感應耦合電	mg/kg	2	n.d.	-
41-7)	漿發射光譜儀分析。(With reference to				
	US EPA 3050B: 1996, analysis was				
	performed by ICP-OES.)				
砷 (As) (Arsenic (As)) (CAS No.: 7440-	参考US EPA 3052: 1996·以感應耦合電漿	mg/kg	2	n.d.	-
38-2)	發射光譜儀分析。(With reference to US				
	EPA 3052: 1996, analysis was performed				
	by ICP-OES.)				

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at https://www.sgs.com.tw/terms-of-service. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

新北市五股區新北產業園區五權七路 25 號 t+886(02)2299 3939 f+886(02)2299 3237 25, Wu Chyuan 7th Road, New Taipei Industrial Park, Wu Ku District, New Taipei City, Taiwan



Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 6 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

測試項目	測試方法	單位	MDL	結果	限值
(Test Items)	(Method)	(Unit)		(Result)	(Limit)
				No.1	
鄰苯二甲酸二丁酯 (DBP) (Dibutyl		mg/kg	50	n.d.	1000
phthalate (DBP)) (CAS No.: 84-74-2)					
鄰苯二甲酸丁苯甲酯 (BBP) (Butyl benzyl		mg/kg	50	n.d.	1000
phthalate (BBP)) (CAS No.: 85-68-7)					
鄰苯二甲酸二(2-乙基己基)酯 (DEHP) (Di-		mg/kg	50	n.d.	1000
(2-ethylhexyl) phthalate (DEHP)) (CAS					
No.: 117-81-7)					
鄰苯二甲酸二異丁酯 (DIBP) (Diisobutyl		mg/kg	50	n.d.	1000
phthalate (DIBP)) (CAS No.: 84-69-5)					
鄰苯二甲酸二異壬酯 (DINP) (Diisononyl		mg/kg	50	n.d.	-
phthalate (DINP)) (CAS No.: 28553-12-					
0, 68515-48-0)					
鄰苯二甲酸二正辛酯 (DNOP) (Di-n-octyl		mg/kg	50	n.d.	-
phthalate (DNOP)) (CAS No.: 117-84-0)	參考IEC 62321-8: 2017,以氣相層析儀/質				
鄰苯二甲酸二異癸酯 (DIDP) (Diisodecyl	譜儀分析。(With reference to IEC 62321-	mg/kg	50	n.d.	-
phthalate (DIDP)) (CAS No.: 26761-40-	8: 2017, analysis was performed by				
0, 68515-49-1)	GC/MS.)				
鄰苯二甲酸二正己酯 (DNHP) (Di-n-hexyl		mg/kg	50	n.d.	-
phthalate (DNHP)) (CAS No.: 84-75-3)					
鄰苯二甲酸二正戊酯 (DNPP) (Di-n-		mg/kg	50	n.d.	-
pentyl phthalate (DNPP)) (CAS No.:					
131-18-0)					
鄰苯二甲酸雙(2-甲氧基乙基)酯 (DMEP)		mg/kg	50	n.d.	-
(Bis(2-methoxyethyl) phthalate (DMEP))					
(CAS No.: 117-82-8)					
鄰苯二甲酸正戊異戊酯 (NPIPP) (N-pentyl		mg/kg	50	n.d.	-
iso-pentyl phthalate (NPIPP)) (CAS No.:					
776297-69-9)					
鄰苯二甲酸二異戊酯 (DIPP) (Diisopentyl		mg/kg	50	n.d.	-
phthalate (DIPP)) (CAS No.: 605-50-5)					



Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 7 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

測試項目	測試方法	單位	MDL	結果	限值
(Test Items)	(Method)	(Unit)		(Result)	(Limit)
				No.1	
聚氯乙烯 (Polyvinyl chloride) (PVC)	參考ASTM E1252: 2013·以傅立葉轉換紅	**	-	Negative	-
	外線光譜儀及焰色法分析。(With				
	reference to ASTM E1252: 2013, analysis				
	was performed by FT-IR and Flame Test.)				

備註(Note):

- 1. mg/kg = ppm; 0.1wt% = 0.1% = 1000ppm
- 2. MDL = Method Detection Limit (方法偵測極限值)
- 3. n.d. = Not Detected (未檢出); 小於MDL / Less than MDL
- 4. "-" = Not Regulated (無規格值)
- 5. **= Qualitative analysis (No Unit) 定性分析(無單位)
- 6. Negative = Undetectable 陰性(未偵測到); Positive = Detectable 陽性(已偵測到)
- 7. 全氟辛烷磺酸及其鹽類包含等物質 (PFOS and its salts including):

CAS No.: 1763-23-1, 2795-39-3, 29457-72-5, 29081-56-9, 70225-14-8, 56773-42-3, 251099-16-8, 307-35-7, 91036-71-4, 4021-47-0 and others.

- 8. 全氟辛酸及其鹽類包含等物質 (PFOA and its salts including):
 - CAS No.: 335-67-1, 335-95-5, 2395-00-8, 335-93-3, 335-66-0, 3825-26-1 and others.
- 9. (#2) =
 - a. 當六價鉻結果大於0.13 μg/cm²·表示樣品表層含有六價鉻。(The sample is positive for Cr(VI) if the Cr(VI) concentration is greater than 0.13 μg/cm². The sample coating is considered to contain Cr(VI).)
 - b. 當六價鉻結果為n.d. (濃度小於0.10 μg/cm²),表示表層不含六價鉻。(The sample is negative for Cr(VI) if Cr(VI) is n.d. (concentration less than 0.10 μg/cm²). The coating is considered a non-Cr(VI) based coating)
 - c. 當六價鉻結果介於 0.10 及 0.13 μg/cm² 時,無法確定塗層是否含有六價鉻。(The result between 0.10 μg/cm² and 0.13 μg/cm² is considered to be inconclusive unavoidable coating variations may influence the determination.)



Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 8 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

10. ▲: MDL是針對元素/測試化合物之評估。(The MDL was evaluated for element / tested substance.) 換算公式 (Conversion Formula): AX = A × F

AX	A	F
氧化雙三丁基錫 (Bis(tributyltin)oxide) (TBTO)	三丁基錫 (Tributyl Tin) (TBT)	1.0276
三氧化二銻 (Antimony trioxide) (Sb ₂ O ₃)	銻 (Antimony)	1.1971

參數換算表 (Parameter Conversion Table):

https://eecloud.sgs.com/Region_TW/DocDownload.aspx#otherDoc

11. 除非另有說明·參照ILAC-G8:09/2019·採用簡單二元(w=0)允收規則進行符合性判定;根據此規則·符合性結果之判定係以測試結果與限值做比較。(Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019. According to this rule, the judgement of conformity is based on the comparing test results with limits.)



Test Report


號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 9 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

重金屬流程圖 / Analytical flow chart of heavy metal

根據以下的流程圖之條件,樣品已完全溶解。(六價鉻測試方法除外)

These samples were dissolved totally by pre-conditioning method according to below flow chart. (Cr^{6+} test method excluded)






Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 10 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

多溴聯苯/多溴聯苯醚分析流程圖 / Analytical flow chart - PBBs/PBDEs






Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 11 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

六溴環十二烷分析流程圖 / Analytical flow chart - HBCDD






Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 12 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

鹵素分析流程圖 / Analytical flow chart - Halogen






Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 13 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

全氟化合物(包含全氟辛酸/全氟辛烷磺酸/其相關化合物等等)分析流程圖 / Analytical flow chart – PFAS (including PFOA/PFOS/its related compound, etc.)





Test Report


號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 14 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

分析流程圖 / Analytical flow chart

【適用於:多氯聯苯、多氯奈、多氯三聯苯、滅蟻靈、氯化石蠟、DBBT】

*Apply to: PCBs, PCNs, PCTs, Mirex, Chlorinated Paraffins, DBBT






Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 15 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

有機錫分析流程圖 / Analytical flow chart - Organic-Tin






Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 16 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

聚氯乙烯物質判定分析流程圖 / Analysis flow chart - PVC






Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 17 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

元素以 ICP-OES 分析的消化流程圖 (Flow chart of digestion for the elements analysis performed by ICP-OES)

根據以下的流程圖之條件,樣品已完全溶解。 / These samples were dissolved totally by pre-conditioning method according to below flow chart.



鋼,銅,鋁,焊錫 / Steel, copper, aluminum, solder	王水,硝酸,鹽酸,氫氟酸,雙氧水 / Aqua regia, HNO ₃ , HCl, HF, H ₂ O ₂
玻璃 / Glass	硝酸,氫氟酸 / HNO ₃ ,HF
金,鉑,鈀,陶瓷 / Gold, platinum, palladium, ceramic	王水 / Aqua regia
銀 / Silver	硝酸 / HNO₃
塑膠 / Plastic	硫酸,雙氧水,硝酸,鹽酸 / H ₂ SO ₄ , H ₂ O ₂ , HNO ₃ , HCl
其他 / Others	加入適當的試劑至完全溶解 / Added appropriate reagent to total digestion



Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022

頁數(Page): 18 of 20


復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

元素(含重金屬)分析流程圖 / Analytical flow chart of elements (Heavy metal included)

根據以下的流程圖之條件,樣品已完全溶解。

These samples were dissolved totally by pre-conditioning method according to below flow chart.

【參考方法/Reference method: US EPA 3051A、US EPA 3052】



* US EPA 3051A 方法未添加氫氟酸 / US EPA 3051A method does not add HF.




Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 19 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

可塑劑分析流程圖 / Analytical flow chart - Phthalate

【測試方法/Test method: IEC 62321-8】






Test Report

號碼(No.): ETR22903699 日期(Date): 03-Oct-2022 頁數(Page): 20 of 20

復盛精密工業股份有限公司 (FUSHENG ELECTRONICS CORPORATION) 新竹縣寶山鄉新竹科學工業園區工業東九路17號 (NO. 17, INDUSTRY E. 9TH RD., SCIENCE PARK HSIN-CHU, TAIWAN, R.O.C.)

* 照片中如有箭頭標示,則表示為實際檢測之樣品/部位. * (The tested sample / part is marked by an arrow if it's shown on the photo.)

ETR22903699



** 報告結尾 (End of Report) **